

ECODESIGN INFORMATION

According to Regulation EU No 327/2011 of the European Commission, implementing Directive 2009/125/CE of European Parliament
Apply to fans

SODECA, S.L.U.

www.sodeca.com

ERP: Performance at the best efficiency point (BEP).

MC	Measurement category
EC	Efficiency category
VSD	Variable Speed Drive
SR	Specific ratio

[m³/h]	Flow rate
[Pa]	Static pressure or total (depending on EC)
[RPM]	Rotation per minute

ηe [%]	Efficiency
N	Efficiency grade
[kw]	Input power

Model	MC	EC	VSD	SR	ηe[%]	N	[kW]	[m ³ /h]	[Pa]	[RPM]
HCT/MAR-35-2T					Non soumis. Atmosphères corrosives					
HCT/MAR-35-4T					Non soumis. Atmosphères corrosives					
HCT/MAR-40-2T-1.5 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-40-4T-0.33					Non soumis. Atmosphères corrosives					
HCT/MAR-45-2T-2 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-45-2T-3 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-45-4T-0.5					Non soumis. Atmosphères corrosives					
HCT/MAR-50-4T-0.75					Non soumis. Atmosphères corrosives					
HCT/MAR-56-4T-0.75					Non soumis. Atmosphères corrosives					
HCT/MAR-56-4T-1 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-56-4T-1.5 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-56-4T-2 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-56-6T-0.33					Non soumis. Atmosphères corrosives					
HCT/MAR-56-6T-0.5					Non soumis. Atmosphères corrosives					
HCT/MAR-56-6T-0.75					Non soumis. Atmosphères corrosives					
HCT/MAR-63-4T-1 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-63-4T-1.5 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-63-4T-2 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-63-4T-3 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-63-4T-4 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-63-6T-0.5					Non soumis. Atmosphères corrosives					
HCT/MAR-63-6T-0.75					Non soumis. Atmosphères corrosives					
HCT/MAR-63-6T-1 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-71-4T-1.5 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-71-4T-2 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-71-4T-3 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-71-4T-4 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-71-6T-0.75					Non soumis. Atmosphères corrosives					
HCT/MAR-71-6T-1 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-71-6T-1.5 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-80-4T-3 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-80-4T-4 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-80-4T-5.5 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-80-6T-1 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-80-6T-1.5 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-80-6T-2 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-80-6T-3 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-90-4T-4 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-90-4T-5.5 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-90-4T-7.5 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-90-4T-10 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-90-6T-2 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-90-6T-3 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-90-6T-4 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-100-4T-7.5 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-100-4T-10 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-100-4T-15 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-100-4T-20 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-100-6T-3 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-100-6T-4 IE3					Non soumis. Atmosphères corrosives					
HCT/MAR-100-6T-5.5 IE3					Non soumis. Atmosphères corrosives					